



GEMASTIREN K60

60% Calcium Carbonate filled Polystyrene Compound

Description

Gemastiren K60 is 60% Calcium Carbonate (CaCO₃) filled Polystyrene compound. The advantages of Gemapilen series are less moulding shrinkage, high degradation temperature under load, high impact resistance, better surface characteristics and greater efficiency depending on heat transmission.

Applications

Gemastiren K60 is specifically designed for thermoforming and injection molding applications. The recommended percentages for Thermoforming is between 10% - 20% and for injection molding between 10% - 20% depending on the application. This ratio can vary according to the machine's specifications, material thickness and the kind of raw material used.

- Thermoforming
- Injection Moulded Parts
- Extrusion

Physical Properties	Değer Value	Birim Unit	Metod Method
Melt Flow Rate (230 C ; 2.16 kg) Erime Akış Oranı	1 - 2	g/10 dk. g/10 min.	ISO 1133
Density Yoğunluk	1.64 - 1.66	g/cm ³	ISO 1183
Ash Content Kül Değeri	60 – 61	%	ISO 3451
Humidity Nem	0.01	%	ISO 787

Storage and Handling

For easy handling and storage, Gemapilen FK is supplied as cylindrical pellets packed into 25kg. bags (55 bags per pallet) or bulk bags (1.000kg.). The storage location should be dry and dust free. The ambient temperature should not exceed 50°C otherwise it can lead to a degradation of the product, which can result in colour changes, odour and effect product performance.

Important

Information contained in this Technical Data Sheet is given in good faith and to the best of the knowledge of GEMA ELEKTRO PLASTİK A.Ş. Before using the product mentioned herein, customers and other users should take all care in determining the suitability of this product for its intended purposes and particularly with regards to conformity with current regulations. It is the customer's responsibility to inspect and test our products in order to satisfy themselves as to the suitability of the product for their and their customer's particular purposes. GEMA ELEKTRO PLASTİK A.Ş does not accept any liability whatsoever arising from the use of this information, or, the use, application or processing of any product described herein.

Gema Polimer Plastik Ürünleri San. ve Tic. A.Ş

Oto Sanayi Sitesi Dalgıç Sokak
No:31 4.Levent İstanbul TURKEY
Tel: +90 212 270 6644 (3 hat)
Fax: +90 212 284 3574

Gema Elektro Plastik A.Ş

Ege Serbest Bölgesi Bahar Sok.
No:21/A Gazemir İzmir/Turkey
Tel: +90 232 252 3723
Fax: +90 232 258 0011

www.gemapolimer.com
info@gemapolimer.com

